

**From:** B. KINEIDER      **To:** Herr SCHULLER

**Object:** PHOTO viewing glass dated 02/27/03<sup>2</sup>

Dear Mr. Schuller,

Enclosed photographs (\*) of the 3 test pieces:

**Conditions:** 24 hours / NaOH 0,1N / 140°C

The three pieces (Boro Plus / B270 / Boro) were immersed simultaneously and in an upright position in 800ml of the fluid.

**Observations:**

After 24 hours the weight result is not yet conclusive due to a coating on two test pieces.

1. BORO : remains transparent and bright.
2. B270 : Early stage of a developing coating, which was scraped off. Slightly dull.
3. BORO Plus : Early stage of a developing coating, which was scraped off. Very dull.

\* *2 normal photographs and 4 enlarged photographs.*

Further test are being conducted.

Sincerely,  
Annelise Christmann.